

(12) UK Patent Application (19) GB (11) 2 217 742 A (13)  
(43) Date of A publication 01.11.1989

(21) Application No 8809820.7

(22) Date of filing 26.04.1988

(71) Applicant  
T & N Technology Limited  
(Incorporated in the United Kingdom)

Cawston House, Cawston, Rugby, Warwickshire,  
CV22 7SB, United Kingdom

(72) Inventors  
Alan William Atkinson  
Jody Keith Burnett

(74) Agent and/or Address for Service  
D D E Newman  
T & N Plc, Bowdon House, Ashburton Road, West,  
Trafford Park, Manchester, M17 1RA, United Kingdom

(51) INT CL.  
F16J 15/10

(52) UK CL (Edition J)  
D1P PDK P1245 P1323  
F2B B1B B1H  
U1S S1782

(56) Documents cited  
None

(58) Field of search  
UK CL (Edition J) D1P PA PB PCBA PDK PDV PDX  
PE PK, F2B  
INT CL. F16J

(54) Improving the water resistance of articles containing fine vermiculite

(57) Certain articles required to function in air at temperatures of 250°C or higher comprise very fine particles of vermiculite from which the interstitial magnesium ions have been at least partially removed and which has been swollen in water. These articles are not ordinarily exposed to water when in use, but if they are they are likely to disintegrate quickly because of the ready dispersibility of the vermiculite particles. By the invention, water-resistance is given to such articles by treating them with a solution of an aluminate salt eg  $\text{NaAlO}_2$  or a zirconyl salt eg  $\text{ZrOCl}_2$ .

GB 2 217 742 A

- 1 -

Improving the water resistance of fine-vermiculite articles

This invention is concerned with improving the water-resistance of fine-vermiculite articles.

Certain articles required to function in air at temperatures of 250°C or higher comprise very fine particles of chemically exfoliated vermiculite (CEV), that is to say vermiculite from which the interstitial magnesium ions have been at least partially removed and which has been swollen in water. Examples of such articles are: a heat shield consisting of foil obtained by evaporation of an aqueous colloidal dispersion of the particles; a rigid foam whose high content of CEV enables the foam to confer a substantial degree of protection against fire on whatever it is attached to; and the sealing element of a gasket for the exhaust system of an internal combustion engine, said element being composed of thermally exfoliated vermiculite whose relatively coarse particles are bound together by CEV particles.

Once put into use, these articles are not ordinarily exposed to water; but if they are, then they are likely to disintegrate quickly or at least lose the fine particles of CEV that are important to their performance at elevated temperature, because the particles - having a diameter of the order of only  $100\text{ }\mu\text{m}$  - are readily dispersed by water.

According to the present invention, there is provided a process for improving the water-resistance of an article which comprises very fine particles of vermiculite from which the interstitial magnesium ions have been at least partially removed and which has been swollen in water, in which process the article is brought into contact with a solution of an aluminate or a zirconyl salt.

Preferably, the salt employed is an alkali metal aluminate, particularly  $\text{NaAlO}_2$  or  $\text{KAlO}_2$ . If a zirconyl salt is used, it is preferably a halide, such as  $\text{ZrOCl}_2$ .

A further improvement in water-resistance can be obtained by a subsequent treatment with a solution of a silicone elastomer.

The invention has particular utility in improving the water-resistance of articles comprising gas-exfoliated vermiculite bound together by CEV particles. By 'gas-exfoliation' we include both the exfoliation by steam

that occurs when raw vermiculite exfoliates on being flash heated and the exfoliation by oxygen that occurs when raw vermiculite is treated with acidic hydrogen peroxide.

The invention is further illustrated by the Examples given later, in the first four of which there is described the effect of various solutions on strips of fine-vermiculite material prepared as follows:

The following ingredients were mixed with moderate shear to form a stiff paste:

Thermally exfoliated vermiculite (MANDOVAL superfine grade, passing a 2mm sieve)	1 kg
--	------

CEV (WR GRACE GP923; 18% aqueous dispersion); enough to give vermiculite solids =	1 kg
---	------

The paste was spread with a blade onto fine polypropylene gauze to give a layer 2mm thick, which was dried in an oven at 130°C. During drying a second gauze was laid on top of the layer. After drying, both gauzes were stripped from the dry vermiculite foil which had been formed, leaving surfaces with a fine pattern of disruption through which waterproofing agents could penetrate.

The foil had mass per unit area of  $600\text{g/m}^2$ , and was pressed to a sheet of thickness 0.6mm and density  $1000\text{kg/m}^3$ . Strips measuring 80 x 25mm were cut from the sheet for use in the Examples.

#### EXAMPLE 1

A strip was immersed for 30 minutes in an aqueous solution of sodium aluminate ( $\text{NaAlO}_2$ ; 1M solution) at room temperature. The strip was then rinsed in water for 10 minutes and dried in an oven at  $130^\circ\text{C}$ . Uptake of the aluminate (dry weight) was 2.5% by weight of the strip.

The strip was allowed to stand exposed to the laboratory atmosphere at ambient temperature for 1 day to allow absorption of moisture to equilibrium, and its tensile strength was measured. It was then immersed in water at room temperature for 48 hours, and then submitted while still wet to measurement of tensile strength. Results are compared below with those for untreated strip and those for strip treated with aluminium sulphate solution (1M).

	Dry (equilibrium) <u>tensile strength</u>	Wet tensile strength <u>after 48 hrs immersion</u>
Untreated strip	0.5 MPa	Disintegrat
Strip treated with 1M- $\text{Al}_2(\text{SO}_4)_3$	0.6 MPa	0.1 MPa
Strip treated with 1M- $\text{NaAlO}_2$	1.4 MPa	0.3 MPa

Treatment with aqueous 1M- $\text{KAlO}_2$  gave results substantially identical with those shown for the sodium salt.

#### EXAMPLE 2

Following generally the procedure of Example 1, a strip was treated with an aqueous solution of zirconyl chloride ( $\text{1M-ZrOCl}_2$ ) and then tested. Results were:

	Dry (equilibrium) <u>tensile strength</u>	Wet tensile strength <u>after 48 hrs immersion</u>
Untreated strip	0.5 MPa	Disintegrated
Strip treated with 1M- $\text{ZrOCl}_2$	0.5 MPa	0.3 MPa

EXAMPLE 3

This Example illustrates the extent to which the improved wet strength imparted by  $\text{NaAlO}_2$  and  $\text{ZrOCl}_2$  treatments is retained after several hours heating.

Tensile strength (MPa) after		
8 hours at 300°C		
	Dry	Wet, after 72 hrs cold $\text{H}_2\text{O}$ immersion
Untreated strip	0.67	Disintegrated
Treated ( $\text{NaAlO}_2$ ) strip	1.63	0.23
Treated ( $\text{ZrOCl}_2$ ) strip	0.92	0.20

EXAMPLE 4

This Example illustrates the further improvement in wet strength which can be obtained by a post-treatment with a silicone elastomer.

The dry product of Example 1 was impregnated with a 15% by weight solution in toluene of the silicone elastomer sold under the name CONFORMAL<sup>R</sup> (Dow Corning) C173DC1 (R-4-3117). The impregnated strip (silicone solids uptake,

3% by weight) was dried, and after an initial pre-cure heating (10 minutes at 50-70°C) was cured by heating at 130°C for 30 minutes. Results of strength testing were:

		<u>After silicone treatment</u>	
<u>Dry tensile strength</u>		Tensile strength	Tensile strength
before	after	after	after
		3 days	8 hours
silicone	silicone	immersion	at 300°C
<u>treatment</u>	<u>treatment</u>	<u>cold H<sub>2</sub>O</u>	<u>Dry 3 days H<sub>2</sub>O</u>
1.40 MPa	2.20 MPa	0.60 MPa	2.24 0.58

#### EXAMPLE 5

This Example illustrates the improvement in strength obtainable in a strip 25-75 $\mu$ m thick of chemically exfoliated vermiculite cut from a foil prepared by evaporation at ambient temperature of a dilute (5% solids) aqueous dispersion of the material (GP923) specified in Example 1.



Treatment was by immersion for 4 hours in a 7% by weight solution of  $\text{NaAlO}_2$ . Results of strength tests were:

	<u>Dry tensile strength</u>	Wet tensile strength after 2 hours <u>H<sub>2</sub>O immersion</u>
Untreated strip	8 MPa	Disintegrated
Treated ( $\text{NaAlO}_2$ ) strip	12-16 MPa	0.1 - 0.5 MPa

CLAIMS

1. A process for improving the water-resistance of an article which comprises very fine particles of vermiculite from which the interstitial magnesium ions have been at least partially removed and which has been swollen in water, in which process the article is brought into contact with a solution of an aluminate or a zirconyl salt.
2. A process according to claim 1, in which the salt employed is an alkali metal aluminate.
3. A process according to claim 2, in which the salt is sodium or potassium aluminate.
4. A process according to claim 1, in which the salt employed is zirconyl chloride.
5. A process according to any of claims 1 to 4, in which the treated article is given a subsequent treatment with a solution of a silicone elastomer.
6. A process according to claim 1, substantially as herein described with reference to Example 1.

7. A process according to claim 1, substantially as herein described with reference to Example 2.
8. A process according to claim 1, substantially as herein described with reference to Example 4.
9. A process according to claim 1, substantially as herein described with reference to Example 5.

